



TECHNICAL DATA

TRIBRID® Polymer

Application temperature +5°C to +40°C
Flow/sag < 3mm
Skin cure 23°C 50% R.H. 25 minutes ±5 min
Full cure time 23°C 50% R.H. 2-3mm/12hrs
 (Due to the versatility of CT1 and the multitude of diverse applications, both internally and externally, the curing time can vary). 3-6 mm/12-48hrs
 6-12mm/48-72hrs

	Colours	Clear + Silver
Density ISO 1183-1	1.58kg/Ltr	1.04kg/Ltr
E-Modulus 100%	1.15 N/mm ²	0.64 N/mm ²
Volume shrinkage after cure:	<3%	<3%
Hardness – DIN 53505:	55° Shore A	42° Shore A
Tensile strength :	290 N/mm ² (2.90 Mpa)	160 N/mm ² (1.60 Mpa)
Thermal stability:	-40°C to + 120°C	

Elongation at rupture
DIN 53504-S1 385% 500%
Frost Resistance during transport: Up to -15°C
Curing system: Neutral Cure

Non Toxic
EC1 Plus Certified A+ Indoor Air Comfort GOLD®
ISEGA Food Preparation Certificate
ETAG 022

Chemical resistance
Good: Water, seawater, aliphatic solvents, oils, greases, Diluted organic acids.

Moderate: Esters, Ketones, Aromatics, Chlorine for swimming pools chlorinated solvents.

Limitations: Strong Acids and Alkalis

Dirt attachment: Practically none

Shelf life: 18 months

- 1) Measured to ISO 9040
- 2) Measured to DIN 53504-S1
- 3) Measured to DIN 53505

All above tests according to ISO 11.600 25HM
 ETAG 022 Annex E,B & Additional tests of Annex F.



APPLICATIONS

For all applications, including construction, engineering, roofing, repair & maintenance, installation and marine repair CT1 replaces: Wood and P.U. adhesives, silicone sealants, sanitary silicone sealants, acrylic sealants and butyl rubber sealants.

As a universal adhesive CT1 bonds to all metals (including lead), glass, mirrors, all woods, MDF, polystyrene, fibreglass, tiles, concrete, most stones (without staining), most synthetic materials, plastics (excluding PP, PE and PTFE).

On mirror applications apply in vertical strips (Not suitable for PP backed mirrors). CT1 works on natural stone (does not bleed through), polyester, polystyrene foam, wet surfaces, even under water.

CT1 Clear and Silver are used predominantly internally and all colours have become the professionals' choice in large scale infrastructure projects.

CT1 can also be painted but must be fully cured and is paintable with all common water-based paints (not suitable with Alkyd Paints). For best results prior testing is recommended.

For application advice on powder coated substrates contact powder coating manufacturer.

DIRECTION FOR USE:

Before use ensure the cartridge has been stored at room temperature

Cut the Cartridge at the nose

Cut off nozzle at desired dimensions

Use a Mastic Gun

Apply on a clean, degreased surface

Finish off the joints with MULTISOLVE

AVAILABLE COLOURS: Clear, white, black, grey, beige, brown, oak, blue, silver & anthracite.

CT1: DELIVERY FORM 290ml Cartridges